

## MANUFACTURE OF SEMICONDUCTOR LASER

## MANUFACTURE OF SEMICONDUCTOR LASER

Patent Number: JP2283084  
Publication date: 1990-11-20  
Inventor(s): FUJII TAKUYA; others: 01  
Applicant(s): FUJITSU LTD  
Requested Patent: ☐ JP2283084  
Application Number: JP19890105059 19890425  
Priority Number(s):  
IPC Classification: H01S3/18  
EC Classification:  
EC Classification:  
Equivalents:

### Abstract

**PURPOSE:** To avoid a thermal deformation and to form an optical guide layer thereon while maintaining the height of a protrusionlike diffraction grating provided on a substrate at a predetermined value by vapor growing at a low temperature by an atomic layer epitaxial growth (ALE) method.

**CONSTITUTION:** Part 31 of an InGaAsP layer for forming an optical guide layer 3 is formed on an InP substrate 1 provided with a diffraction grating 2, the grating 2 is covered therewith, and the residue 32 of the layer 3, an active layer 4 and a clad layer 5 are then sequentially formed by a normal MOVPE method. The grating 2 is not thermally deformed at 400 deg.C, and not thermally deformed at 400-650 deg.C after it is covered with an InGaAsP layer 31. Accordingly, the grating can preserve a predetermined height of the state provided initially on the substrate. The residue 32 of the layer and the other layer 4, the layer 5, etc., are formed by a normal MOVPE method..